

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) EP 1 073 090 A2

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
31.01.2001 Bulletin 2001/05

(51) Int. Cl.⁷: H01J 31/12, H01J 9/02

(21) Application number: 00305791.6

(22) Date of filing: 07.07.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• Lee, Cheol-Jin
Gunsan-City, Jeonlabuk-do (KR)
• Yoo, Jae-Eun
Seongbuk-gu, Seoul (KR)

(30) Priority: 27.07.1999 KR 9930698
31.05.2000 KR 0029579

(74) Representative:
Browne, Robin Forsythe, Dr.
Urquhart-Dykes & Lord
Tower House
Merrion Way
Leeds LS2 8PA West Yorkshire (GB)

(71) Applicant:
Iljin Nanotech Co., Ltd.
Seoul (KR)

(54) Field emission display device using carbon nanotubes and manufacturing method thereof

(57) A field emission display device, and a manufacturing method thereof are provided. In the field emission display device, a first metal film for use as a cathode is formed on a lower substrate. A dielectric film pattern and a second metal film pattern are formed on the first metal film, each of which has a plurality of fine holes which expose the first metal film. Each of the fine holes can have a diameter of 0.5 to 10.0 μm . A conductive high polymer film is formed within the fine holes. Carbon nanotubes for use as emitter tips are vertically arranged within the conductive high polymer film. A spacer is installed on the second metal film pattern. An upper substrate, to which a transparent electrode and a fluorescent material are attached, is positioned on the spacer. Accordingly, the FED device using carbon nanotubes can be simply manufactured with a large area by a method of forming fine holes in a second metal film and a dielectric film and putting carbon nanotubes in the fine holes.

EP 1 073 090 A2

Description

BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001] The present invention relates to a field emission display (FED) device and a manufacturing method thereof, and more particularly, to an FED device using carbon nanotubes and a manufacturing method thereof.

2. Description of the Related Art

[0002] In general field emission display (FED) devices, when several hundreds of positive volts are applied to an external gate electrode with respect to a conic silicon emitter tip, electrons are emitted from the end portion of the emitter tip affected by a strong electric field, and the emitted electrons collide with an anode to which several kilovolts to several hundreds of kilovolts are applied and which is coated with a fluorescent material. In this way, the FED devices act as display devices. However, in a conventional FED device using silicon emitter tips, which are made by etching a silicon substrate, there is difficulty in separating an anode from a cathode at a fine interval of about 1.0 to 1.5nm. Also, in a conventional FED device, leakage current is high, the reliability and performance are degraded, and a manufacturing yield is low, due to deterioration of silicon tips caused by a very high operating voltage and a high current emission. An FED device using carbon nanotubes has been proposed as an improvement on the FED device using silicon emitter tips.

[0003] Conventional carbon nanotubes are synthesized by an electrical discharge method or a laser deposition method, and put in a cleaning solution and shaken by an ultrasonic washer to be refined. The refined carbon nanotubes are implanted into the pores of a porous ceramic filter to apply the refined carbon nanotubes to an FED device. Then, the carbon nanotubes contained in the pores of the porous ceramic filter are stamped and stood upright on conductive polymer on a lower substrate for an FED device, thereby forming emitter tips.

[0004] The FED device using conventional carbon nanotubes as an emitter tip excels in stability compared to an FED device using silicon emitter tips. However, the FED device using conventional carbon nanotubes has difficulty in efficiently standing carbon nanotubes on the conductive polymer, and its manufacturing method is complicated. Thus, the FED device using conventional carbon nanotubes has a low manufacturing yield, and cannot be manufactured to have a large area.

SUMMARY OF THE INVENTION

[0005] An objective of the present invention is to provide a field emission display (FED) device using car-

bon nanotubes, which can be manufactured to have a large area, and which has a high density of tips per unit area.

[0006] Another objective of the present invention is to provide a method of manufacturing an FED device which can be manufactured to have a large area by a simple manufacturing process.

[0007] Accordingly, to achieve the first objective, the present invention provides a field emission display device including a first metal film for use as a cathode formed on a lower substrate; and a dielectric film pattern and a second metal film pattern formed on the first metal film, each of which has a plurality of fine holes which expose the first metal film. The lower substrate can be formed of glass, quartz, silicon or alumina (Al_2O_3). The first metal film can be formed of chrome, titanium, tungsten or aluminum, and the second metal film pattern can be formed of chrome, titanium or palladium. Each of the fine holes can have a diameter of 0.5 to 10.0 μm . A conductive high polymer film is formed within the fine holes. Carbon nanotubes for use as emitter tips are vertically arranged within the conductive high polymer film. A spacer is installed on the second metal film pattern. An upper substrate, to which a transparent electrode and a fluorescent material are attached, is positioned on the spacer.

[0008] To achieve the second objective, the present invention provides a method of manufacturing a field emission display device. In this method, a first metal film for use as a cathode is formed on a lower substrate. A dielectric film is formed on the first metal film. A second metal film for use as a gate electrode is formed on the dielectric film. A dielectric film pattern and a second metal film pattern, each of which has a plurality of fine holes which expose the first metal film, are formed by patterning the second metal film and the dielectric film. A liquid conductive high polymer film is formed within the fine holes. Carbon nanotubes for use as emitter tips are sprayed into the fine holes and vertically arranged. Here, the carbon nanotubes are stood upright within the fine holes by ultrasonic vibration or voltage application. The liquid conductive high polymer film is cured, and then a spacer is installed on the second metal film pattern. An upper substrate, having a transparent electrode and a fluorescent material attached thereto, is attached to the spacer.

[0009] An FED device using carbon nanotubes according to the present invention as described above can be simply manufactured to have a large area by a method of forming fine holes in a second metal film and a dielectric film and putting carbon nanotubes into the fine holes.

BRIEF DESCRIPTION OF THE DRAWINGS

[0010] The above objectives and advantages of the present invention will become more apparent by describing in detail a preferred embodiment thereof with

reference to the attached drawings in which:

FIG. 1 is a cross-sectional view of a field emission display (FED) device using carbon nanotubes according to the present invention; and
FIGS. 2 through 4 are cross-sectional views illustrating a method of manufacturing the FED display of FIG. 1.

DESCRIPTION OF THE PREFERRED EMBODIMENT

[0011] Hereinafter, an embodiment of the present invention will be described in detail with reference to the attached drawings. However, an embodiment of the present invention to be described later can be modified into various other forms, and the scope of the present invention must not be interpreted as being restricted to the described embodiment. The embodiment is provided to more completely explain the present invention to those skilled in the art. In drawings, the thicknesses or sizes of layers or regions are exaggerated for clarity. Like reference numerals in the drawings denote the same members. Also, when it is written that a layer is formed "on" another layer or a substrate, the layer can be formed directly on the other layer or the substrate, or other layers can intervene therebetween.

[0012] Referring to FIG. 1, a field emission display (FED) display using carbon nanotubes according to the present invention has a first metal film 32 for use as a cathode formed on a lower substrate 30. The lower substrate 30 is formed of glass quartz, silicon or alumina Al_2O_3 . The first metal film 32 is formed of chrome, titanium, tungsten or aluminum. A dielectric film pattern 34a and a second metal film pattern 36a, each of which has a plurality of fine holes which expose the first metal film 32, are formed on the first metal film 32. The second metal film pattern 36a can be formed of chrome, titanium or palladium, and is used as a gate electrode in an FED device. The fine holes can be formed to have a diameter of 0.5 to 10.0 μm .

[0013] A conductive high polymer film 42 is formed within the fine holes, and carbon nanotubes 44 are arranged vertically within the conductive high polymer film 42. The carbon nanotubes 44 are used as emitter tips. These vertically-arranged carbon nanotubes 44 can obtain a great amount of emission current at a low operating voltage, for example, about 1.5V/ μm . Also, the vertically-arranged carbon nanotubes 44 can increase luminous efficiency since they have a high density of tips per unit area. A spacer 48 is installed on the second metal film pattern 36a, and an upper substrate 50, to which a transparent electrode 52 for an anode and a fluorescent material 54 are attached, is provided on the spacer 48. An electric field is applied between the first metal film 32 serving as a cathode and the transparent electrode 52 serving as an anode, so that electrons are emitted from the vertically-arranged carbon nanotubes 44. The emitted electrons collide with

the fluorescent material 54, so that the FED device having such a structure emits red, green and blue light. At this time, an electric field is applied between the second metal film pattern 36a for the gate electrode and the first metal film 32 for a cathode, so that electrons easily collide with the fluorescent material 54. Consequently, the FED device according to the present invention is a three-electrode FED device.

[0014] FIGS. 2 through 4 are cross-sectional views illustrating a method of manufacturing the FED display of FIG. 1. FIG. 2 illustrates the step of forming a first metal film 32, a dielectric film 34 and a second metal film 36 on a lower substrate 30. To be more specific the first metal film 32 serving as a cathode is formed to a thickness of 0.2 to 0.5 μm on the wide lower substrate 30. The lower substrate 30 is formed of glass, quartz, silicon or alumina (Al_2O_3). The first metal film 32 is formed of chrome, titanium, tungsten or aluminum. Next, the dielectric film 34 is formed to a thickness of 1 to 5 μm on the first metal film at a low temperature. Continuously, the second metal film 36 serving as a gate electrode is formed to a thickness of 0.2 to 0.5 μm on the dielectric film 34. The second metal film 36 is formed of chrome, titanium or palladium by an electron-beam deposition method or a thermal deposition method.

[0015] FIG. 3 illustrates the step of forming a second metal film pattern 36a and a dielectric film pattern 34a, each of which has fine holes 40, by patterning the second metal film 36 and the dielectric film 34. To be more specific, the second metal film 36 is coated with a photoresist film (not shown) having a thickness of 1.5 to 2.0 μm , and the photoresist film is developed, thereby forming a photoresist pattern 38. Next, the second metal film 36 and the dielectric film 34 are etched using the photoresist pattern 38 as a mask, thereby forming the second metal film pattern 36a and the dielectric film pattern 34a. Here, a plurality of fine holes 40 are formed to expose the first metal film 32. The fine holes 40 each have a diameter of about 0.5 to 10.0 μm , and are separated from each other at intervals of about 2.0 to 15.0 μm .

[0016] FIG. 4 illustrates the step of forming a conductive high polymer film 42 and positioning carbon nanotubes 44 within the fine holes 40. To be more specific, the conductive high polymer film 42 is formed by filling 1/3 of each of the fine holes 40 of the dielectric film 34 with liquid conductive high polymer. For example, the conductive high polymer can be a carbon adhesive or a silver adhesive.

[0017] Next, carbon nanotubes 44 for use as emitter tips are sprayed into the fine holes 40 by ultrasonic vibration, voltage impression, or the like, and are vertically oriented on the first metal film 32. In other words, after the carbon nanotubes 44 are sprayed on the fine holes 40, ultrasonic vibration is applied, a voltage is applied between the upper and lower portions of the lower substrate 30, or the two methods are both performed on the resultant structure. In this way, the carbon

nanotubes are effectively injected and stood upright in the conductive high polymer film 42 within the fine holes 40. As a result, the carbon nanotubes 44 are vertically aligned in the conductive high polymer film 42 on the first metal film 32. The vertically-oriented carbon nanotubes 44 can obtain a great amount of emission current at a low operating voltage, for example, at about 1.5 V/ μm . Also, the vertically-oriented carbon nanotubes 44 provide excellent luminous efficiency since they have a high density of tips per unit area.

[0018] Continuously, the liquid conductive high polymer film 42 on which the carbon nanotubes 44 have been sprayed is cured at 400°C or less, preferably, at 300 to 400°C.

[0019] Then, as shown in FIG. 1, a spacer 48 is installed to a length of about 100 to 700 μm on the second metal film pattern 36a. Next, the transparent electrode 52 serving as an anode is formed on the upper substrate 50, and a fluorescent material 54, which emits light when bombarded by electrons, is then attached to the transparent electrode 52. A glass substrate is used as the upper substrate 50, and an indium tin oxide (ITO) electrode can be used as the transparent electrode.

[0020] Thereafter, the upper substrate 50 to which the transparent electrode 52 and the fluorescent material 54 are attached is turned upside down and put on the spacer 48, and then vacuum is sealed and mounted, thereby completing the formation of the FED device.

[0021] An FED device using carbon nanotubes according to the present invention as described above can be simply manufactured with a large area by a method of forming fine holes in a second metal film and a dielectric film, and putting carbon nanotube in the fine holes.

[0022] Also, the FED device according to the present invention can obtain a great amount of emission current at a low operating voltage, for example, at about 1.5V/ μm , since it uses carbon nanotubes which is vertically oriented well as emitter tips. Also, the FED device according to the present invention provides excellent luminous efficiency, high reliability, and high yield since it has a high density of tips per unit area.

Claims

1. A field emission display device comprising:

a first metal film for use as a cathode formed on a lower substrate;
a dielectric film pattern and a second metal film pattern formed on the first metal film, each of which has a plurality of fine holes which expose the first metal film;
a conductive high polymer film formed within the fine holes;
carbon nanotubes for use as emitter tips, vertically arranged within the conductive high polymer film;

a spacer installed on the second metal film pattern; and

an upper substrate to which a transparent electrode and a fluorescent material are attached, the upper substrate formed on the spacer.

2. The field emission display device of claim 1, wherein the lower substrate is formed of glass, quartz, silicon or alumina (Al_2O_3).

3. The field emission display device of claim 1, wherein the first metal film is formed of chrome, titanium, tungsten or aluminum, and the second metal film pattern is formed of chrome, titanium or palladium.

4. The field emission display device of claim 1, wherein each of the fine holes has a diameter of 0.5 to 10.0 μm .

5. A method of manufacturing a field emission display device, the method comprising:

forming a first metal film for use as a cathode on a lower substrate;

forming a dielectric film on the first metal film;

forming a second metal film for use as a gate electrode on the dielectric film;

forming a dielectric film pattern and a second metal film pattern, each of which has a plurality of fine holes which expose the first metal film, by patterning the second metal film and the dielectric film;

forming a liquid conductive high polymer film within the fine holes;

spraying carbon nanotubes for use as emitter tips into the fine holes and vertically arranging the carbon nanotubes;

curing the liquid conductive high polymer film;

installing a spacer on the second metal film pattern; and
attaching an upper substrate, having a transparent electrode and a fluorescent material attached thereto, to the spacer.

6. The method of claim 5, wherein the lower substrate is formed of glass, quartz, silicon or alumina (Al_2O_3).

7. The method of claim 5, wherein the first metal film is formed of chrome, titanium, tungsten or aluminum, and the second metal film is formed of chrome, titanium or palladium.

8. The method of claim 5, wherein the carbon nanotubes are stood upright within the fine holes by ultrasonic vibration or voltage impression.

9. The method of claim 5, wherein each of the fine holes has a diameter of 0.5 to 10.0 μm .

10. The method of claim 5, wherein the liquid conductive high polymer film is cured at 300 to 400°C.

5

10

15

20

25

30

35

40

45

50

55

5

FIG. 1




FIG. 2




FIG. 3





FIG. 4





Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 073 090 A3**

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
16.04.2003 Bulletin 2003/16

(51) Int Cl.7: **H01J 9/02, H01J 31/12**

(43) Date of publication A2:
31.01.2001 Bulletin 2001/05

(21) Application number: 00305791.6

(22) Date of filing: 07.07.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• Lee, Cheol-Jin
Gunsan-City, Jeonlabuk-do (KR)
• Yoo, Jae-Eun
Seongbuk-gu, Seoul (KR)

(30) Priority: 27.07.1999 KR 9930698
31.05.2000 KR 2000029579

(74) Representative: Browne, Robin Forsythe, Dr.
Urquhart-Dykes & Lord
Tower House
Merrion Way
Leeds LS2 8PA (GB)


(71) Applicant: Iljin Nanotech Co., Ltd.
Seoul (KR)

(54) Field emission display device using carbon nanotubes and manufacturing method thereof

(57) A field emission display device, and a manufacturing method thereof are provided. In the field emission display device, a first metal film (32) for use as a cathode is formed on a lower substrate (30). A dielectric film pattern (34a) and a second metal film pattern (36a) are formed on the first metal film, each of which has a plurality of fine holes which expose the first metal film. Each of the fine holes can have a diameter of 0.5 to 10.0 μm . A conductive high polymer film (42) is formed within the

fine holes. Carbon nanotubes (44) for use as emitter tips are vertically arranged within the conductive high polymer film. A spacer (48) is installed on the second metal film pattern. An upper substrate (50), to which a transparent electrode (52) and a fluorescent material (54) are attached, is positioned on the spacer. Accordingly, the FED device using carbon nanotubes can be simply manufactured with a large area by a method of forming fine holes in a second metal film and a dielectric film and putting carbon nanotubes in the fine holes.

FIG. 1



EP 1 073 090 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 30 5791

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	GEIS M W ET AL: "DIAMOND GRIT-BASED FIELD EMISSION CATHODES", IEEE ELECTRON DEVICE LETTERS, IEEE INC. NEW YORK, US, VOL. 18, NR. 12, PAGE(S) 595-598 XP000727110 ISSN: 0741-3106 * page 595; figure 1A *	1	H01J9/02 H01J31/12
E	EP 1 061 555 A (ILJIN NANOTECH CO LTD ; LEE CHEOL JIN (KR); CHO YOUNG SANG (KR)) 20 December 2000 (2000-12-20) * claim 5 *	1	
A	US 5 695 378 A (YUI ROBERT E ET AL) 9 December 1997 (1997-12-09) * claims 1-12 *	5	
A	EP 0 905 737 A (ISE ELECTRONICS CORP) 31 March 1999 (1999-03-31) * claims 1,11 *	1,5	
A	WO 97 47020 A (CANDESCENT TECH CORP) 11 December 1997 (1997-12-11) * claims 37,43 *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.7) H01J
A	EP 0 712 146 A (COMMISSARIAT ENERGIE ATOMIQUE) 15 May 1996 (1996-05-15) * claims 1,5 *	1,5	
A	EP 0 724 280 A (NIPPON ELECTRIC CO) 31 July 1996 (1996-07-31) * claim 1 *	5	
A	EP 0 834 897 A (SGS THOMSON MICROELECTRONICS) 8 April 1998 (1998-04-08) * claims 1,15 *	1,5	
-/-			
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 February 2003	Examiner Van den Bulcke, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 (2.02) (P040201)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 30 5791

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	EP 0 779 642 A (SGS THOMSON MICROELECTRONICS) 18 June 1997 (1997-06-18) * claims 1-7 *	5	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 February 2003	Examiner Van den Bulcke, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 (03.02 (P4/C01))

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 30 5791

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-02-2003

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
EP 1061555	A	20-12-2000	CN	1280382 A	17-01-2001
			EP	1061555 A1	20-12-2000
			JP	2001052652 A	23-02-2001
US 5695378	A	09-12-1997	US	5686782 A	11-11-1997
EP 0905737	A	31-03-1999	JP	11111158 A	23-04-1999
			JP	2000036243 A	02-02-2000
			EP	0905737 A1	31-03-1999
			JP	11167886 A	22-06-1999
			US	6239547 B1	29-05-2001
WO 9747020	A	11-12-1997	US	5865657 A	02-02-1999
			EP	1018131 A1	12-07-2000
			JP	2001506395 T	15-05-2001
			KR	2000016557 A	25-03-2000
			TW	398005 B	11-07-2000
			WO	9747020 A1	11-12-1997
EP 0712146	A	15-05-1996	FR	2726688 A1	10-05-1996
			DE	69510521 D1	05-08-1999
			DE	69510521 T2	16-03-2000
			EP	0712146 A1	15-05-1996
			JP	8241664 A	17-09-1996
			US	5828162 A	27-10-1998
EP 0724280	A	31-07-1996	DE	69622445 D1	29-08-2002
			EP	0724280 A1	31-07-1996
			JP	2956565 B2	04-10-1999
			JP	8273534 A	18-10-1996
			US	5787337 A	28-07-1998
EP 0834897	A	08-04-1998	EP	0834897 A1	08-04-1998
			DE	69621017 D1	06-06-2002
			DE	69621017 T2	31-10-2002
			JP	10188785 A	21-07-1998
			US	6465950 B1	15-10-2002
			US	6036566 A	14-03-2000
EP 0779642	A	18-06-1997	EP	0779642 A1	18-06-1997
			DE	69518849 D1	19-10-2000
			DE	69518849 T2	11-01-2001
			US	6000980 A	14-12-1999

EPO FORM PD439

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.